




Comparison Chart

Natural durability of solid wood according to European norm EN 350

DURABILITY LEVEL	EXT. CLASS 1	EXT. CLASS 2	EXT. CLASS 3	EXT. CLASS 4	EXT. CLASS 5
DURABILITY PERIOD	> 25 Years	15-25 years	10-15 years	5-10 years	< 5 years
WOOD SPECIES	 Burma Teak Doussie	Bangkirai Iroko Mahogany W.Red Cedar	Plantation Teak Douglas Fir Sapele Oak	Okoume Spruce Pine Eur. Larch Limba	White Ash Beech Poplar Red Pine Maple
WITHSTANDS	Outdoor Contact with ground, not protected. Always wet	Outdoor Contact with ground, not protected. Regularly wet	Outdoor Contact with ground, protected. Rarely wet	Indoor and covered areas Dry	Indoors Dry